

Product Description

General	Adalastic 2000 Haftprimer is an abrasion-resistant and chemical-resistant liquid film to 2K polyurethane polyurea. It's main use is as a primer on the Adalastic 2000.
Suitability	As a primer on the Adalastic 2000 to anchor the overlying layers.
Advantages	Adalastic 2000 Haftprimer has a very good tensile and tear strength, and a large elongation. Curing is also at low temperatures, up to + 3°C guaranteed. Adalastic 2000 Haftprimer shows good resistance and is specially used for secondary containments of storage plants for fuels and solvents.

Specification

Mixing ratio	10: 1 by weight
Density of mixture	1.06 kg / dm³
Pot life	35 min at 23°C
Hardening / Recoatability	Walkable after 24 h Fully hardened 20°C 7 days
Colour	Blue, transparent
Packaging	Units of 15 / 1,5 kg
Storage Life	12 months in originally sealed containers at ambient temperature
Art. No.	Comp. A W-D9119 Comp. B W-D9120

Application	
Subsurfaces	Mineral base-surfaces shall be solid, clean, and dry. Concrete surfaces shall be clean, grease-free and preferably grit blasted.
Structures	Priming-coats on concrete: Adagrund, Adaflex BG, Adaflex FU sanded off. Priming-coats on asphalt: Adaflex BG spez. sanded off. Priming-coats on steel: Adagrund.
Mixing	Add the contents of the comp. B container completely to the comp. A container, clean out if necessary with a rubber spatula and mix the combination thoroughly for 3 min. with a stirrer. Depends on temperature shall be added 3 – 6% of Verdünner 102.
Processing	Adalastic 2000 Haftprimer is preferably applied with a spreader, but if needed it can also be applied with a roller. After application air shall be freed from the coating using a spiked roller and the coating smoothed off.
Equipment needed	Hand-stirring machine or power-drill with stirrer, hot-air blower, possibly a de-humidifier.
Climatic conditions	The steel surface temperature has to be at min. 3°C and at least 3°C above the dew point at any time during application and hardening!

Safety Precautions	
Precautions to be observed	Safety measures should be taken in accordance with the material safety data sheet. Local legal, health and safety regulations apply.
Liability	The above information is based on numerous tests and many years of experience. Liability for the application of the described product cannot be accepted as the results largely depend on the proper treatment and application of the material.
Hazards information	Comp. A <div data-bbox="683 1639 767 1727" data-label="Image"> </div> Health Hazard

	<div>Comp. B</div> <div>     </div> <div> Health Hazard Fire Exclamation Mark Environment </div>
Transport information	<div>Comp. A UN NO ADR</div> <div>Comp. B UN 1263</div>