

Product Description

General	Epoflex Universal Flickset is thixotropic, solvent-free, two- component, epoxy resin based repair product that is packed “ready-to-use”.
Suitability	Epoflex Universal Flickset serves as a repair kit for repair and levelling of pores after surface coating with Epoflex 6G, Epoflex 6 thix and Epoflex 6N. The Properties of the repair kit (Flickset) correspond to those of the basic product Epoflex 6N.








Specification

Mixing ratio	5: 2 by weight
Packaging	Units of 250 / 100 g
Storage Life	24 months at 10°C - 35°C in originally sealed containers
Art. No.	Comp. A W-D0037-A Comp. B W-D0037-B

Application

Subsurfaces	The subsurface needs to be clean and dry. Hardened coating areas of Epoflex 6G, Epoflex 6 thix or Epoflex 6N are to be sanded for roughness.
Processing	Mix for three minutes and use within 10 minutes. Depending on subsurface temperature, the applied material is walkable after 30 minutes up to 2 hours. Full curing after 2 days. In order to increase efficiency for the repair, it is recommended to mark areas to be repaired with a felt pen.

Safety Precautions

Precautions to be observed	Safety measures should be taken in accordance with the material safety data sheet. Local legal, health and safety regulations apply.				
Liability	The above information is based on numerous tests and many years of experience. Liability for the application of the described product cannot be accepted as the results largely depend on the proper treatment and application of the material.				
Hazards information	Comp. A				
		Fire	Health Hazard	Exclamation Mark	Environment
Hazards information	Comp. B				
		Health Hazard	Exclamation Mark	Corrosion	
Transport information	Comp. A UN 3082 Comp. B UN 3267				