



Product Description	
General	Webaester spezial is a thixotropated, pre-accelerated, epoxide vinyl ester resin with a styrene content of 33%.
Suitability	The system is approved as single wall laminate to be applied on steel (floor refurbishment according to EEMUA159) as well as double wall system for tank lining.
Advantages	The highly interconnected resin has a high heat shape resistance and a remarkable chemicals resistance, in particular against chlorine-containing media and organic solvents.

Specification	
Mixing ratio	100: 1 by weight with MEKP
Density of the mixture	1.1 kg / dm ³
Pot life	20 – 30 min at 20°C – 30 °C
Curing	Wet on wet – if not possible sandpaper slightly the surface
Consumption	2.75 kg / m ² for a layer thickness of 2.5 mm
Colour	Transparent – other colours at request
Packaging	Units of 20 / 0,20 kg
Storage life	12 months at 25°C in originally sealed containers
Art. No.	Comp. A W-D0817

Application	
Subsurfaces	Steel surfaces shall be grid blasted and preferably primered. E.g. Adagrund.
Structure	Multilayer laminate.
Mixing	Put the content of container Comp. B completely into the container of Comp. A and mix everything well for a period of 3 min using a mixer.
Processing	Application and distribution using a synthetic resin roller with a resin temperature of approx. 25°C. Bleed with a grooved roller.
Equipment needed	Manual agitator or drilling machine with mixer, synthetic resin roller, grooved metal roller, fan heater, air dehumidifier, if necessary.
Equipment cleaning	Tools should be cleaned with dissolver L 208 immediately after use; after hardening, the resin can only be removed mechanically.
Climatic conditions	The steel surface temperature has to be at min. 8°C and at least 3°C above the dew point at any time during application and hardening!

Safety Precautions	
Precautions to be observed	Safety measures should be taken in accordance with the material safety data sheet. Local legal, health and safety regulations apply.
Liability	The above information is based on numerous tests and many years of experience. Liability for the application of the described product cannot be accepted as the results largely depend on the proper treatment and application of the material.
Hazards information	<p>Comp. A</p> <div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>Health Hazard</p> </div> <div style="text-align: center;">  <p>Exclamation Mark</p> </div> </div>
Transport information	Comp. A W-D0817